# Vesta Klepsi 045

Product code: VKP045




2020.10 01 | 02

**GMR** ENLIGHTS

Flange VKP045\_F VKP045\_M

Wavy shape steel hot rolling pole, predisposed for the installation lighting fixture Vesta C.

The pole is equipped with M12 screw, AISI 304 stainless steel (grounding).







## **Geometry and mechanical features**

Total height: 4.560 mm Total weight: ① flange: 39 Kg

Toundation: 41 Kg

## Materials | Color

Pole: Hot rolled steel S235 - hot galvanized | EN 10025 - EN1461

Color: Light grey


### Terminal block 4x16mm<sup>2</sup>

Smooth fitting door




# **Fixing type**





Foundation



Supplied: Heat-shrink sheat

Scale: 1:25



# **Protection cycles**

### Protection of galvanized steel surfaces for poles

The protection of galvanized steel elements is achieved by following steps:

- Micro sandblasting
- First epoxy layer application followed by:

Wilting > Drying > Cooling

· Acrylic glaze layer application followed by:

Wilting > Drying > Cooling

• Packing at least after 24-hour-drying at room temperature.

### Protection of galvanized steel surfaces for brackets and pastorals

The protection of the galvanized steel elements is achieved thanks to:

- Micro sandblasting
- Phosphoric pickling bath at a ph level ranging from 1.5 to 3
- · Rinsing with demineralised water
- First powder layer application
- Kiln firing
- Application of a final powder layer
- Kiln roasting of the final powder layer at 180°
- · Cooling.

#### Protection of cast iron surfaces for bases

The protection of cast iron elements is achieved by the following treatments:

- Surface micro shotblasting
- Mono-component dip galvanizing followed by:

Wilting > Drying > Cooling

• Epoxy micaceous primer application followed by:

Wilting > Drying > Cooling

• Acrylic enamel application followed by:

Wilting > Drying > Cooling.

• Packing at least after 24-hour-drying at room temperature.

# Protection of die-cast aluminium surfaces for lighting fixtures, tops, collars, brackets and pastorals

Brackets, pastoral, and die-cast accessories undergo a cycle of powder painting which creates a barrier against the corrosion of metal parts. Moreover this barrier makes the finished product comply with design specifications in terms of surface roughness, color and reflectance. The cycle consists of the following steps:

- Micro sandblasting
- Hot pickling bath in a zinc-based phosphodegreasing solution
- Phospho-chromatation for surfeces clearing
- Washing with water
- Rinsing with demineralised water and subsequent drying
- First bowder layer application followed by kiln baking at 180°
- Final powder layer application using a High Durability product and final kiln roasting at 180°C.



Salt spray test | FLORIDA TEST

The top quality of such treatments is confirmed by the succesfull results of specific salt spray test (all products exceed widely 2.500 hours) and the strictest international tests, among which FLORIDA TEST.

The salt spray test is made in accordance with standard UNI EN ISO 9227.



**GMR ENLIGHTS s.r.l** 

Legal headquarters: Strada Provinciale Specchia - Alessano, 68 • 73040 (LE)

> Administrative and operational headquarters: Via Grande n°226 • 47032 Bertinoro (FC)

> > T+39 0543 462611 F+39 0543 449111

sales@gmrenlights.com www.gmrenlights.com